

# इंटरनेट

# मानक

## Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”


IS 4844 (1968): Method of sampling and preparation of asbestos fibre for laboratory test purposes [CED 53: Cement Matrix Products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”



BLANK PAGE



IS : 4844 - 1968

*Indian Standard*  
METHOD OF SAMPLING  
AND PREPARATION OF ASBESTOS FIBRE  
FOR LABORATORY TEST PURPOSES  
( First Reprint MARCH 1982 )

UDC 677.511:620.113



© Copyright 1969

INDIAN STANDARDS INSTITUTION  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

Price Rs 3<sup>00</sup>

Gr 2

February 1969

# Indian Standard

## METHOD OF SAMPLING AND PREPARATION OF ASBESTOS FIBRE FOR LABORATORY TEST PURPOSES

Cement and Concrete Sectional Committee, BDC 2

*Chairman*

SHRI J. DATT

*Representing*

The Concrete Association of India, Bombay

*Members*

SHRI M. A. MEHTA ( *Alternate to*  
Shri J. Datt )

SHRI A. P. BAGCHI

SHRI P. S. BHATNAGAR

DR S. K. CHOPRA

Sahu Cement Service, New Delhi

Bhakra & Beas Designs Organization, New Delhi

Central Building Research Institute (CSIR),  
Roorkee

SHRI J. S. SHARMA ( *Alternate* )

DIRECTOR ( CSM )

Central Water & Power Commission, New Delhi

DIRECTOR ( DAMS III ) ( *Alternate* )

DR R. K. GHOSH

Indian Roads Congress, New Delhi

DR R. R. HATTIANGADI

The Associated Cement Companies Ltd, Bombay

SHRI V. N. PAI ( *Alternate* )

JOINT DIRECTOR STANDARDS  
( B & S )

Research, Designs & Standards Organization  
( Ministry of Railways )

DEPUTY DIRECTOR STANDARDS  
( B & S ) ( *Alternate* )

SHRI S. B. JOSHI

S. B. Joshi & Co Ltd, Bombay

PROF S. R. MEHRA

Central Road Research Institute (CSIR),  
New Delhi

DR R. K. GHOSH ( *Alternate* )

SHRI S. N. MUKERJI

National Test House, Calcutta

SHRI E. K. RAMACHANDRAN ( *Alternate* )

SHRI ERACH A. NADIRSHAH

Institute of Engineers ( India ), Calcutta

SHRI K. K. NAMBIAR

In personal capacity ( 16 First Crescent, Park Road,  
Madras-20 )

SHRI M. L. NANDA

Central Public Works Department, New Delhi

SUPERINTENDING ENGINEER,  
2ND CIRCLE ( *Alternate* )

BRIG NARESH PRASAD

Engineer-in-Chief's Branch, Army Headquarters,  
New Delhi

SO 1 DESIGN ( PAVEMENT ) ( *Alternate* )

SHRI I. L. PATEL

Directorate General of Supplies & Disposals  
( Ministry of Works, Housing & Supply ),  
New Delhi

SHRI RABINDER SINGH

National Buildings Organization ( Ministry of Works,  
Housing & Supply ), New Delhi

SHRI B. D. AHUJA ( *Alternate* )

( Continued on page 2 )

INDIAN STANDARDS INSTITUTION  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
PROF G. S. RAMASWAMY	Structural Engineering Research Centre (CSIR), Roorkee
DR N. S. BHAL (Alternate)	
SHRI T. N. S. RAO	Gammon India Ltd, Bombay
SHRI S. R. PINHEIRE (Alternate)	
REPRESENTATIVE	Geological Survey of India, Calcutta
REPRESENTATIVE	M. N. Dastur & Co (Pvt) Ltd, Calcutta
REPRESENTATIVE	The India Cements Ltd, Madras
SHRI K. G. SALVI	Hindustan Housing Factory Ltd, New Delhi
SHRI C. L. KASLIWAL (Alternate)	
SECRETARY	Central Board of Irrigation & Power, New Delhi
SHRI S. N. SINHA	Roads Wing (Ministry of Transport)
SHRI KARTIK PRASAD (Alternate)	
SHRI L. SWAROOP	Dalmia Cement (Bharat) Ltd, New Delhi
SHRI A. V. RAMANA (Alternate)	
DR H. C. VISVESVARAYA	Cement Research Institute of India, New Delhi
SHRI R. NAGARAJAN, Director (Civ Engg)	Director General, ISI (Ex-officio Member)

*Secretary*

SHRI Y. R. TANEJA  
Deputy Director (Civ Engg), ISI

**Asbestos Cement Products Subcommittee, BDC 2 : 3**

*Convener*

DR H. C. VISVESVARAYA      Cement Research Institute of India, New Delhi

*Members*

SHRI N. H. BHAGWANANI	Engineer-in-Chief's Branch, Army Headquarters, New Delhi
DEPUTY DIRECTOR (B & S)	Research, Designs & Standards Organization (Ministry of Railways)
ASSISTANT DIRECTOR (B & S) (Alternate)	
ENGINEER OFFICER I (A)	Central Public Works Department, New Delhi
SHRI W. C. MERSEUR	The Asbestos Cement Ltd, Bombay
SHRI K. V. RAMASESHAN (Alternate)	
SHRI V. R. NATARAJAN	Shree Digvijay Cement Co Ltd, Ahmedabad
SHRI I. L. PATEL	Directorate General of Supplies & Disposals (Ministry of Works, Housing & Supply)
SHRI V. PODDAR	Rohtas Industries Ltd, Dalmianagar
SHRI M. P. VERMA (Alternate)	
REPRESENTATIVE	The Hyderabad Asbestos Cement Products Ltd, Hyderabad
SHRI R. S. SHARMA	Geological Survey of India, Calcutta
SHRI N. VENKATARAMAN	Hindustan Ferodo Ltd, Bombay

(Continued on page 5)

# *Indian Standard*

## METHOD OF SAMPLING AND PREPARATION OF ASBESTOS FIBRE FOR LABORATORY TEST PURPOSES

### 0. FOREWORD

**0.1** This Indian Standard was adopted by the Indian Standards Institution on 16 October 1968, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.

**0.2** Sampling and preparation of samples are very important for testing. The procedure for sample preparation adopted here is not similar to other textile fibres, because of different characteristics of asbestos from other textile fibres and all types of asbestos do not have good spinning qualities. Hand mixing is preferred here for gentle rubbing and breaking up of lumps and clods in the samples. Reasonable accuracy in testing will depend on properly mixing of the different samples and also by conditioning the fibre.

**0.3** In the formulation of this standard due weightage has been given to international co-ordination among standards and practices prevailing in different countries in addition to relating it to the practices in the field in this country.

**0.4** In reporting the results of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS : 2-1960\*.

---

### 1. SCOPE

**1.1** This standard covers the method of sampling asbestos fibre and the preparation of the sample from lots for laboratory test purposes. A lot shall be from *one* source.

### 2. SAMPLING

**2.1** The sample shall be selected so as to indicate the true character and condition of the asbestos fibre which it represents.

---

\*Rules for rounding off numerical values (*revised*).

## 2.2 Procedure

**2.2.1** Prepare a 2-kg composite sample from each lot consisting of 200 bags or part thereof by selecting 20 handfuls ( approximately 100 g ) each from different one-twentieth of the lot.

**2.2.2** The sample shall be kept in closed containers placed in covered storage for subsequent testing.

## 3. PREPARATION OF THE SAMPLE

**3.1** Each sample shall first be allowed to be kept under normal work room temperature.

**3.2** The sample shall be spread over dry, smooth and clean area.

**3.3** The sample shall be conditioned by passing the fibres through the hands with gentle rubbing in order to break up and to separate all lumps and clods of fibre.

**3.4** The well mixed sample shall be spread out on a smooth and clean area.

**3.5** In case it is necessary the samples shall be reduced to the size of 2 kg by quartering. This 2-kg sample shall be used as the source of fibre for each individual test.

**3.6** For extraction of samples for test purpose, 2-kg sample shall be spread on a clean surface, quartered and from each quarter desirable size of sample shall be taken.

**3.7** Each individual test result shall be reported separately.

**3.8** The supplier shall supply free of charge the asbestos required for testing.

## 4. CONDITION FOR TESTING

**4.1** The tests shall be carried out in rooms or cabinets provided with a normal climate which involves a temperature of  $27 \pm 2^{\circ}\text{C}$  and relative humidity of  $65 \pm 5$  percent ( see IS : 196-1966\* ).

**4.2 Adjustment of Relative Atmospheric Humidity in Climate Cabinets** — Adjustment of a relative atmospheric humidity of 65 percent in a climate cabinet is best effected by providing a dish containing 35.9 percent sulphuric acid solution ( sp gr 1.262 at  $27^{\circ}\text{C}$  ) of maximum surface area. Circulation of air by means of a slowly rotating ventilator improves the uniformity of the atmosphere by proper distribution of conditioned air throughout the entire cabinet. Attention shall be paid to a sufficiently high degree of temperature regulators constancy (  $\pm 1$  deg ) within the cabinet, if necessary, by introduction of temperature regulator in order to avoid fluctuation of the relative degree of atmospheric humidity.

**4.3** The test specimen shall be then left in the normal atmosphere for 24 hours in such a way to expose, as far as possible, all portions of the specimen.

---

\*Atmospheric conditions for testing.



( Continued from page 2 )

## Panel for Amphibole Variety of Indigenous Asbestos, BDC 2 : 3 : P-1

*Convener*

SHRI R. K. SINHA

*Representing*

Indian Bureau of Mines ( Ministry of Steel, Mines &amp; Metals ), Nagpur

*Members*

DR N. G. BASAK

Central Fuel Research Institute ( CSIR ),  
Jalgaon

SHRI A. K. CHATTERJEE

Central Building Research Institute ( CSIR ),  
Roorkee

SHRI S. KRISHNASWAMY

In personal capacity ( 21 Lakshmi Colony, North  
Crescent Road, Thyagarayanagar, Madras )

SETH PUSALAL MANSINGHKA

Pusalal Mansinghka Pvt Ltd, Bhilwara ( Rajasthan )

SHRI K. M. MATHUR

Indian Standards Institution

SHRI RABINDER SINGH

National Buildings Organization ( Ministry of Works,  
Housing & Supply ), New Delhi

SHRI J. J. SHAH

Shree Digvijay Cement Co Ltd, Ahmedabad

SHRI S. K. SWAMI

Asbestos Cement Ltd, Bombay

SHRI R. THIAGARAJAN

Geological Survey of India, Calcutta

SHRI H. C. VERMA

Associated Instrument Manufacturers ( India ) Pvt  
Ltd, New Delhi

DR I. D. VERMA

Hyderabad Asbestos Cement Products Ltd,  
Hyderabad

SHRI M. P. VERMA

Rohtas Industries Ltd, Dalmianagar

SHRI N. VENKATARAMAN

Hindustan Ferodo Ltd, Bombay

# INTERNATIONAL SYSTEM OF UNITS (SI UNITS)

## Base Units

Quantity	Unit	Symbol
Length	metre	m
Mass	kilogram	kg
Time	second	s
Electric current	ampere	A
Thermodynamic temperature	kelvin	K
Luminous intensity	candela	cd
Amount of substance	mole	mol

## Supplementary Units

Quantity	Unit	Symbol
Plane angle	radian	rad
Solid angle	steradian	sr

## Derived Units

Quantity	Unit	Symbol	Conversion
Force	newton	N	1 N = 1 kg·1 m/s <sup>2</sup>
Energy	joule	J	1 J = 1 N·m
Power	watt	W	1 W = 1 J/s
Flux	weber	Wb	1 Wb = 1 V·s
Flux density	tesla	T	1 T = 1 Wb/m <sup>2</sup>
Frequency	hertz	Hz	1 Hz = 1 c/s (s <sup>-1</sup> )
Electric conductance	siemens	S	1 S = 1 A/V
Pressure, stress	pascal	Pa	1 Pa = 1 N/m <sup>2</sup>

## INDIAN STANDARDS INSTITUTION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones : 26 60 21, 27 01 31

Telegrams : Manaksanstha

### Regional Offices:

		Telephone
Western : Novelty Chambers, Grant Road	BOMBAY 400007	37 97 29
Eastern : 5 Chowringhee Approach	CALCUTTA 700072	23-08 02
Southern : C. I. T. Campus, Adyar	MADRAS 600020	41 24 42

### Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur	AHMADABAD 380001	2 03 91
'F' Block, Unity Bldg, Narasimharaja Square	BANGALORE 560002	2 76 49
Gangotri Complex, Bhadbhada Road, T.T. Nagar	BHOPAL 462003	6 27 16
22E Kalpana Area	BHUBANESHWAR 751014	5 36 27
Ahimsa Bldg, SCO 82-83, Sector 17C	CHANDIGARH 160017	2 83 20
5-8-56C L. N. Gupta Marg	HYDERABAD 500001	22 10 83
D-277 Todarmal Marg, Banipark	JAIPUR 302006	6 98 32
117/418 B Sarvodaya Nagar	KANPUR 208005	8 12 72
Patliputra Industrial Estate	PATNA 800013	6 28 08
Hantex Bldg (2nd Floor), Rly Station Road	TRIVANDRUM 695001	32 27